



Polypropylene (PP) - Random Copolymers - Extrusion - RP340R

Property	Unit	Test	Value
M	g/10 min	ASTM D1238	25
Density	K	ASTM D1505	0.9
Flexural Modulus	MPa	ASTM D790	1050
Tensile Strength at Yield	MPa	ASTM D638	28
Tensile Elongation at Yield	%	ASTM D638	12
I	J/m	ASTM D256	65
Rockwell Hardness	R Scale	ASTM D785	94
Vicat softening point (10N)		ASTM D1525	127
H.D.T. (0.46 Mpa)		ASTM D648	83
A	hours	ASTM D3012	360
Haze (1mm)	%	ASTM D1003	22
Gloss (60?)	---	ASTM D2457	73