



Polypropylene (PP) - Random Copolymers - Extrusion - MR230C

Property	Unit	Test	Value
M	g/10min	D 1238 L	0.4-0.6
Hardness Rockwell			
Linear coefficient of Expansion	m	D 696	0.11
T			0.89
Specific gravity		D 792	
Mechanical properties			
Flexural modulus	MPa	D 790	9.5
Tensile strength at yield	MPa	D 638	28
Elongation at break	%	D 638	>430
Notched Izod impact strenght	J/m	D 256	NB
Unnotched Izod imp.strenght	J/m	D 256	NB
Vicat softening point (9.8N)		D 1525	135
H.D.T. (0.45 Mpa)		D 648	80
A	hours	D 3012	>9,000