



## Polypropylene (PP) - Random Copolymers - Extrusion - RP300D

Property	Unit	Test	Value
M	g/10 min	ISO 1133	0.6
Density	K	ISO 1183	0.9
Flexural Modulus	MPa	ISO 527-1, -2	1000
Tensile Strength at Yield (50 mm/min)	MPa	ISO 527-1, -2	25
Tensile Elongation at Yield (50 mm/min)	%	ISO 527-1, -2	10
Flexural Modulus (2 mm/min)	Mpa	ISO 178	1100
Charpy impact strength (notched) at 23°C	Kj/m2	ISO 179	20
Melting temperature	°C	ISO 3146	148