



Polypropylene (PP) - Heterophasic Copolymers - Injection Molding - EP440G

Property	Unit	Test	Value
M	g/10 min	ISO 1133	1.3
Density	K	ISO 1183	0.9
Flexural Modulus	MPa	ISO 527-1, -2	1450
Tensile Strength at Yield	MPa	ISO 527-1, -2	27
Tensile Elongation at Break	%	ISO 527-1, -2	> 50
Tensile Elongation at Yield	%	ISO 527-1, -2	8
Charpy impact strength (Notch A)		ISO 179	
2	K		40
0	K		9
G	-----	DIN 67530	65