



General Purpose Poly Styrene (GPPS) - GPPS 1047

Property	Unit	Test	Value
M	g/10min	D1238	3.8
STYRENE RESIDUAL MONOMER	PPM	CLG LABPSG004 (ATOFINA TEST METHOD)	<500
V		D1525	99
TENSILE STRENGTH	MPA	D638	50
CHARPY IMPACT STRENGTH	Kj/m2	D256	10
FLEXURAL MODULUS	MPa	D790	3100