



General Purpose Poly Styrene (GPPS) - GPPS 44

Property	Unit	Test	Value
M	g/10min	D1238	14
STYRENE RESIDUAL MONOMER	PPM	CLG LABPSG004 (ATOFINA TEST METHOD)	<500
V		D1525	90
TENSILE STRENGTH	MPa	D638	40
CHARPY IMPACT STRENGTH	Kj/m2	D256	8
FLEXURAL MODULUS	MPa	D790	2900