



Expandable Poly Styrene (EPS) - HS321

Property	Unit	Test	Value
BEAD SIZE	MM	SUNPOR 7.2.5 (MIN 90% BY WT)	(0.7-1)(>90%wt)
K-VALUE		SUNPOR 7.2.4	55
PENTANE CONTENT	WT%	SUNPOR 7.2.2	5.20%
BULK DENSITY	KG/M3	SUNPOR 7.2.3	18-30
RESIDUAL MONOMER	PPM	SUNPOR 7.2.1	500