



Styrene Butadiene Rubber (SBR) - 1502

Property	Unit	Test	Value
Mooney viscosity (ML 1+4 @ 100 oC)	MU	ASTM D1646	46-58
M	MU	ASTM D1646	<84
Volatile matters	% wt.	ASTM D5668	< 0.75
Total ash	% wt.	ASTM D5667	< 1.5
Organic acids	% wt.	ASTM D5774	4.5 -7
Soaps	% wt.	ASTM D5774	< 0.5
Bounded styrene	% wt.	ASTM D5775	22.5-24.5
T	k	ASTM D 412	>250
U	%	ASTM D 412	>350
3	k	ASTM D 412	167-207