



## Epoxy Resins(ER) - E-06

Property	Unit	Test	Value
Appearance	visual	visual	clear light yellow liquid
Epoxy equivalent	g/eq	ASTM D1652	185-196
Epoxy value	mol/100g	ASTM D1652	0.51-0.54
Color	Pt-Co (APHA)	ASTM 1209(APHA)	Max 100
Viscosity	Mpas	DIN 53015 (@25 C)	<15000
Hydrolysable Chlorine	%wt	ASTM 1726	Max 0.2
Non-Volatile	%wt	DIN EN ISO 3251	Min 99