



Epoxy Resins(ER) - E-06 SPL

Property	Unit	Test	Value
Appearance	visual	visual	clear light yellow liquid
Epoxy equivalent	g/eq	ASTM D1652	185-192
Epoxy value	mol/100g	ASTM D1652	0.52-0.54
Color	Pt-Co (APHA)	ASTM 1209	Max 50
V	Mpas	DIN 53015	10,000-14,000
Hydrolysable Chlorine	%wt	ASTM 1726	Max 0.1
Non-Volatile	%wt	DIN EN ISO 3251	Min 99.3