



## Epoxy Resins(ER) - E-X75 LC

Property	Unit	Test	Value
Appearance	visual	visual	clear light yellow liquid
Epoxy equivalent	g/eq	ASTM D1652	434-555
Epoxy value	mol/100g	ASTM D1652	0.180-0.230
Color	Pt-Co (APHA)	ASTM 1209(APHA)	Max 40
Viscosity	Mpas	D	6000-12000
Hydrolysable Chlorine	%wt	ASTM 1726	Max 0.1
%Non-Volatile	%wt	DIN EN ISO 3251	74-76