



## Acrylonitrile Butadiene Styrene (ABS) - SD0150

Property	Unit	Test	Value
M	GR/10miin	ASTM D-1238	1.8
IZOD IMPACT STRENGTH	KGF.CM/CM	ASTM D-256	22
VICAT SOFTENING POINT(5KGF LOAD)		ASTM D-1525	98
TENSILE STRENGTH AT YEILD	KGF/CM2	ASTM D-638 (5mm/min)	450
FLEXURAL STRENGTH AT YEILD	KGF/CM2	ASTM D-790	600
FLEXURAL MODULUS	KGF/CM2	ASTM D-790	22000
R	R.SCALE	ASTM D-785	105