



High Density Polyethylene (HDPE) - Film - 7000F

Property	Unit	Test	Value
D	g/cm ³	ISO 1183	0.952
M	g/10min	ASTM D1238	0.04
M	g/10min	ASTM D1238	
Stress at Yield Point	kg/cm ²	ASTM D638	250
Stress at break	kg/cm ²	ASTM D638	390
Elongation at break	%	ASTM D638	Above 500
Izod impact	kg.cm/cm	ASTM D256	30
Stress Cracking Resistance	hr	ASTM D1693	Above 600
Melting point		ASTM D2117	131