



Low Density Polyethylene (LDPE) - Film - LD2420F

Property	Unit	Test	Value
Melt Flow Rate (2.16kg)			0.75
Density			923
Tensile Modulus			260
Tensile Strength at Yield			11
Tensile Strength at Break MD/TD			26/20
Tensile Strain at Break MD/TD			300/600
Dart Drop Impact (50 blown film)			150
V			96
Haze (50)			< 8.0
G			> 90