



Linear Low Density Polyethylene (LLDPE) - Film - LL0209AA

Property	Unit	Test	Value
Resin			
M	G/10MIN	D 1238	0.9
DENSITY	GR/CM3	D2839	0.92
VICAT SOFTENING POINT		D1525	100
FILM*			
TENSILE STRENGTH @ YIELD,MD/TD	Mpa	D 638	10.5/11
ELONGATION @BREAK ,MD/TD	%	D 638	620/840
TENSILE STRENGTH @ BREAK ,MD/TD	Mpa	D 688	41/32
TEAR STRENGTH ,MD/TD	gr/25mic	D 1922	145/370
IMPACT STRENGTH ,DART	gr/25mic	D1709	150
HAZE	%	D1003	10
G	Rating	D2457	56