



Linear Low Density Polyethylene (LLDPE) - Film - LL0220KJ

Property	Unit	Test	Value
M	gr/10min	ASTM D 1238	2.3
Density	gr/cm ³	ASTM D 1505	0.92
Haze	%	ASTM D 1003	12
G	%	ASTM D 2457	30
Anti Oxidant			?
Anti Block			?
Slip Agent			?
Dart Drop Impact	g	ASTM D 1709(A)	90
Tear Strength MD/TD	gr/25?m	ASTM D 1922	100/300
Tensile Strength at yield MD/TD	MPa	ASTM D 882	10:11
Tensile Strength at Break MD/TD	Mpa	ASTM D 882	30/25
Elongation at break MD/TD	%	ASTM D 882	1000/1100
Secant Modulus MD/TD	Mpa	ASTM D 882	80/100
Coefficient of friction		ASTM D 1894	0.13
Vicat Softening Temperature		ASTM D 1525	100
Melting Point		BPC	123